

# Paintworks Specification NZ 305.1

**System**            **Wattyl Estapol Speed Gloss / Satin**

**Substrate**        **Interior – New timber**

**Category**        **General purpose –Wattyl Estapol Speed Gloss/Satin**

**Product Features**

Wattyl Estapol Speed Gloss / Satin is a tough acrylic polymer clear for use on interior timber, offering a quick drying, low odour, non-yellowing coating system. It is also suitable for use on MDF board, or as a sealer on oily timbers for Wattyl Estapol Polyurethane Gloss, Satin or Matt clear.

**Surface Preparation**

Ensure the surface is dry and free of dirt or grease. Fill nail holes or cracks with Wattyl Colourwood Wood Stop Putty (WA163) in a matching colour. Allow to dry.

Application Details	Data Sheet	Coverage m <sup>2</sup> /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat <b>Wattyl Estapol Speed Gloss / Satin</b> <i>(equipment: brush or spray)</i>	WA184- 5	10-14	83	28-40	30 minutes	3 hours
Second Coat: <b>Wattyl Estapol Speed Gloss / Satin</b> <i>(equipment: brush or spray)</i>	WA184- 5	10-14	83	28-40	30 minutes	3 hours

**Recommended Uses**

For interior use only.  
Suitable for use on interior timber wall panelling, joinery, doors, and furniture etc.  
**Not** suitable for exterior use or on extreme wear areas such as floors, bench tops or surfaces subjected to direct heat or that are constantly wet such as bathrooms. For interior areas of extreme wear use Wattyl Estapol Easy Floor Clear Water Based (WA187).  
Ideal for use on light coloured timbers such as Pine, Ash, Western Red Cedar and MDF board.

**Additional Notes**

**Do not** Do not apply excessively heavy coats to horizontal surfaces as this will extend the through-dry time of the product, which may result in it being lifted by subsequent coats.

**Caution**

Provide adequate ventilation during use.  
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

- This information is provided with respect to the listed Wattyl products. Wattyl recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the (MSDS) and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
- Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.
- To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.