

Paintworks Specification NZ 320.5

System Watty Colourwood Pigmented Stain over coated with Watty Estapol Speed Gloss/Satin

Substrate Interior – New timber

Category General Purpose – Pigmented stain / water based polyurethane clear.

Product Features

Watty Colourwood Pigmented Stain is semi transparent pigment based type stain suitable for interior use on all timbers and veneers. Ideal for Whitewood, MDF, Particle Board and Pine

Watty Estapol Speed Gloss/Satin is an interior clear polyurethane finish that is suitable for all interior timbers.

Surface Preparation

Minimum Surface Preparation. Ensure the surface is dry and free of dirt or grease. Fill nail holes or cracks with Watty Colourwood Wood Stop Putty (WA163) in a matching colour. Allow to dry. Sand thoroughly in the direction of the timber grain.

Application Details	Data Sheet	Coverage m ² /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: Watty Colourwood Dye Stain (equipment: clean cloth pad)	WA161	10-14	N/A	N/A	30 minutes	4 hours
Second Coat Watty Estapol Speed Gloss/Satin (equipment: brush)	WA184	10-14	71 to 100	27-38	2 hours	6 hours
Third Coat: Watty Estapol Speed Gloss/Satin (equipment: brush)	WA184	10-14	71 to 100	27-38	2 hours	6 hours

Recommended Uses For interior use only.
Suitable for interior application such as built-in furniture, wall panelling, window frames, doors, kitchens cupboards.

Additional Notes **Not suitable** for use on MDF Board.
Do not use on timber floors as it may highlight surface imperfections and result in uneven colour. Some timbers particularly natives such as Rimu, Totara and Matai are best sealed after staining with Watty Estapol Speed Satin to prevent slow drying of turpentine based polyurethanes

Caution Provide adequate ventilation during use.
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Watty products. Watty recommends that:

- (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
2. The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.
3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Watty Office.
4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.