

Paintworks Specification NZ 355.1

System	Wattyl Forestwood Decking Stain
Substrate	Exterior – New timber
Category	Timber Decking System –turps based oil fortified semi clear stain.

Product Features

A see-through, oil fortified stain for exterior timber decks, verandas and pergolas in new or good condition. Wattyl Forestwood Decking Stain adds natural colour whilst penetrating the timber to preserve and protect. Ideal for use on durable softwoods and close grained hardwoods used for decking and related applications. Available in a range of pre-mixed factory colours and exciting tinted colours. Wattyl Forestwood Decking Stain enhances the natural beauty of the timber, allowing the grain pattern to show through. It must be regarded as a maintainable coating with less life expectancy than opaque paint. For a longer life, solid cover, water-based finish for new, older or weathered timbers, use Taubmans TimberProof Acrylic Low Sheen (TA022).

Surface Preparation – Refer to section 4 of the Wattyl Specifiers Manual

Minimum Surface Preparation. Ensure all new timber is dry and free of mould, dirt or grease. Fill nail holes or cracks with suitable exterior grade putty. Allow to dry. Sand smooth and remove dust. Galvanised nails should be used to avoid rust staining.

Application Details	Data Sheet	Coverage m ² /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: Wattyl Forestwood Decking Stain <i>(equipment: brush, speedbrush)</i>	WA152	4-12	N/A	N/A	4 hours	24 hours
Second Coat (optional) Wattyl Forestwood Decking Stain <i>(equipment: brush, speedbrush)</i>	WA152	4-12	N/A	N/A	4 hours	24 hours

Recommended Uses
For exterior use on bare timber only.
Suitable for use on exterior timber decking, sundecks, verandahs, pergolas and other exterior timber areas. Ideal for use on durable softwood and close grained hardwood.

Additional Notes
Not suitable for previously primed, painted, badly weather or damaged timber.

Caution
Provide adequate ventilation during use.
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

- This information is provided with respect to the listed Wattyl products. Wattyl recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the Material Safety Data Sheet (MSDS) and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
- Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.
- To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.