

Paintworks Specification NZ 365.1

System	Wattyl Forestwood Linseed Oil Fence Stain
Substrate	Exterior – New and Previously Stained timber fences and retaining walls
Category	Timber Fence Stain System –turps based linseed oil fortified semi clear stain.

Product Features

A semi-transparent natural oil stain designed to enrich the colour and grain of both rough sawn and dressed fencing timbers.

Surface Preparation – Refer to section 4 of the Wattyl Specifiers Manual

Minimum Surface Preparation.

New Timber: Allow new to timber weather for 2 months before staining. Ensure the timber is dry and free from dirt, wax, grease or oil. To thoroughly clean the surface, use a mixture of household detergent and warm water, then rinse off with clean water. The surface must be completely dry before applying Wattyl Forestwood Linseed Oil Fence Stain.

Previously Oiled Timber: Remove as much mould growth as possible by scraping and stiff brushing. Apply a mixture of 1L hypochlorite bleach and 20ml Liquid sugar soap in 3L of water by spray or brush, leave for 30 minutes then hose off and allow the surface to dry. Alternatively a proprietary fungicidal wash may be used as directed.

Allow to dry thoroughly before re applying Wattyl Forestwood Linseed Oil Fence Stain

Application Details	Data Sheet	Coverage m ² /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat:						
Wattyl Forestwood Linseed Oil Fence Stain <i>(equipment: brush, speedbrush)</i>	WA155	4-12	N/A	N/A	4 hours	24 hours
Second Coat (optional)						
Wattyl Forestwood Linseed Oil Fence Stain <i>(equipment: brush, speedbrush)</i>	WA155	4-12	N/A	N/A	4 hours	24 hours

Recommended Uses

Wattyl Forestwood Linseed Oil Fence Stain should only be used on bare timber or over previously oil stained surfaces. Do not apply over paint or onto surfaces other than timber.

Maintenance: We recommend regular (at least annual) washing of the surface to remove surface contaminants with a mixture of 250 mls mould killer, 20 mls Liquid sugar soap, and 4 litres of water applied with a soft brush. Hose off and allow the surface to dry.

Forestwood Linseed Oil Fence Stain must be regarded as a maintainable coating and should be re applied every summer or as soon as the timber shows signs of weathering due to exposure.

Additional Notes Not suitable for previously primed, painted, badly weather or damaged timber.

Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the Material Safety Data Sheet (MSDS) and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.

4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.