

Paintworks Specification NZ 210.3

System Taubmans Butex Gloss Enamel

Substrate Exterior - New and unpainted timber

Category Premium – Turps Based Enamel

Product Features

Taubmans Butex Gloss Enamel is a high quality, hard wearing gloss finish with outstanding durability and washability. This product flows out to give a smooth even surface.

Surface Preparation. Refer to section 4 of the Wattyl Specifiers Manual

Minimum surface preparation. Ensure all new timber is dry, clean, and free from dirt, dust or grease. Fill cracks or holes with a suitable exterior grade putty. Allow to dry, sand smooth and remove dust.

Application Details	Data Sheet	Coverage m ² /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: Taubmans Underproof Wood Primer <i>(equipment: brush)</i>	TA003	8-14	71-125	44-78	4 hours	16 hours
Second Coat: Taubmans Underproof All Purpose Undercoat <i>(equipment: brush, roller or spray)</i>	TA004	8-14	71-125	39-68	4 hours	24 hours
Third Coat: Taubmans Butex Gloss Enamel <i>(equipment: brush, roller or spray)</i>	TA024	14-16	63-71	34-39	4 hours	24 hours

Recommended Uses For interior or exterior use.
For use on suitably prepared timber, galvanised iron, bare steel and previously painted surfaces.

Additional Notes Oily timbers such as Rimu, Totara and Matai may cause drying problems. We recommend priming these surfaces with Taubmans UnderProof Acrylic Primer Undercoat

Caution Radiata Pine and other knotted / high resin timbers have knots which can shrink and loosen and resin bleed may occur. Selecting a colour with an LRV greater than 40% will help minimise damage and resin bleed caused by excessive heat absorption.
Provide adequate ventilation during use.
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

- This information is provided with respect to the listed Wattyl products. Wattyl recommends that:
 - you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product;
 - the product be used only in accordance with the information provided by Wattyl;
 - the product be transported, stored and handled in accordance with the information on the (MSDS) and relevant TDS; and
 - you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
- Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.
- To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.