

Paintworks Specification NZ 225.6

System Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel

Substrate Exterior - New and unpainted masonry, brick, cement render, fibre cement sheets etc

Category Premium – Water Based Acrylic Enamel

Product Features

Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel is an advanced formulation acrylic with enamel-like characteristics for interior and exterior use. It combines the smooth finishing properties and serviceability of enamels with the low odour, quick dry, and convenience of water based finishes.

Surface Preparation. Refer to section 4 of the Watty Specifiers Manual

Minimum Surface Preparation. Allow all new cementitious substrates to fully cured prior to painting. Typically this may take a minimum of 4-6 weeks. The substrate must be free of dirt, dust, grease, oil, mould release agents, bondbreakers, laitance and any other contaminants that may interfere with adhesion. Fill holes and cracks with a suitable filling compound, block down, sand to an even finish, dust off.

Fresh cementitious substrates should be left a minimum of 28 days before coating. There must be less than 15% moisture wood equivalent in the surface at the time of application to ensure optimum coating performance. To achieve a uniform finish on very porous masonry surfaces e.g blockwork, it is necessary to apply a coat of Taubmans UnderProof Undercoat & Wallboard Sealer before the topcoats.

| Application Details | Data Sheet | Coverage m ² /L | Film Thickness (microns) | | Dry Times (minimum) | |
|-----------------------------------------------------------------------------------------------------------------------------------|------------|-------------------------------|-----------------------------|-------|------------------------|------------|
| | | | Wet | Dry | Touch | Recoat |
| First Coat: Taubmans UnderProof Acrylic Primer Undercoat <i>(equipment: brush, roller or spray)</i> | TA002 | 8-14 | 71 to 125 | 28-49 | 30 minutes | 2 hours |
| Second Coat: Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel <i>(equipment: brush, roller or spray)</i> | TA047-49 | 14-16 | 71-63 | 23-26 | 30 minutes | 4 hours |
| Third Coat: Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel <i>(equipment: brush, roller or spray)</i> | TA047-49 | 14-16 | 71-63 | 23-26 | 30 minutes | 4 hours |

Recommended Uses For interior and exterior use.
Suitable for use on suitably prepared timber Doors, Windows and Trim.

Additional Notes **Note:** Not recommended for exterior weather boards.

Caution Provide adequate ventilation during use.
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.

4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.