

System	Taubmans Easyflo Q.D. Satin Enamel
Substrate	New interior paper faced plasterboard
Area	Walls – Wet service areas Walls – Wet service areas: Ventilated Ceilings – Wet service areas: Ceilings - Wet Service Areas: Ventilated
Gloss levels	Satin
Category	Trade Premium - Turps Based Enamel
Description	Taubmans Easyflo Q.D. Satin Enamel is quick drying enamel for interior use, specially designed for airless spray and brush application. It produces a durable, hard abrasion and moisture resistant finish, with excellent opacity and surface smoothness. It has excellent scrub-ability and stain removal properties, allows frequent cleaning.

**Surface Preparation: Refer to Section 4 of the Watty! Specifiers Manual**

Minimum surface preparation: Ensure the surface is clean and dry. Fill any holes or surface imperfections with a suitable filler. Sand the filled areas and all surface smooth; wipe down to remove sanding dust. Do not sand the uncoated paper faced plasterboard.

Application recommendations	Data Sheet	Coverage m <sup>2</sup> /L	Film thickness (microns)		Dry times (minimum hrs)	
			Wet	Dry	Touch	Recoat
First coat applied by brush, roller or spray (must be back rolled)						
Taubmans Easyflo Q.D. Enamel Undercoat	TA014	8 - 14	70 – 125	35 - 61	2	8
Second coat applied by brush, roller, spray, airless spray						
Taubmans Easyflo Q.D. Satin Enamel	TA056	14 - 16	60 – 70	28 - 32	2	6
Third coat applied by brush, roller, spray, airless spray						
Taubmans Easyflo Q.D. Satin Enamel	TA056	14 - 16	60 – 70	28 - 32	2	6

Recommended uses: For interior use only on properly sealed or undercoated paper faced plasterboard. Ideal for ceilings in ventilated wet areas such as bathrooms, laundries and kitchens. Especially suitable in commercial applications where speed of finishing and low odour is required.

Additional notes: Leave for seven days after application of final coat before washing. Avoid using household cleaners containing high level of ammonia for a period of 2 weeks after application of the enamel. Dry times are measured at 20°C and 65% humidity, lower temperatures and higher humidity will prolong these times by up to 100%.

Caution Provide adequate ventilation during use. Application should not be carried out if the air or substrate temperature is below 10°C or above 35°C, or the humidity is greater than 85%. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Watty! products. Watty! recommends that:  
(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty!; (c) the product be transported, stored and handled in accordance with the information on the (MSDS) and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.  
2. The information in this technical data sheet was prepared using information gathered during product development. While Watty! endeavours to update this information and maintain the accuracy and currency of its contents, Watty! cannot guarantee that the information provided is wholly comprehensive.  
3. Watty! recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Watty! Office.  
4. To the full extent permitted by law, Watty!'s liability for breach of a condition or warranty implied into the contract for sale between Watty! and you by law is limited at Watty!'s election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.