

Paintworks Specification NZ 012.1

System Taubmans LivingProof Eggshell / Satin / Silk

Substrate Interior - Previously painted interior oil based/enamel finishes

Category Premium – Water Based

Product Features

Taubmans LivingProof Eggshell / Satin / Silk is a 100% acrylic wall paint with superior feel and appearance, excellent covering power and adhesion, applies with minimum roller spatter, superior scrubability together with excellent stain removal properties, scuff resistance, outstanding durability and washability

Surface Preparation. Refer to section 4 of the Wattyl Specifiers Manual

Minimum Surface Preparation. Ensure the surface is clean and dry. All loose, peeling and flaking material must be removed with a scraper. Remove all gloss on painted surfaces with 220 abrasive paper. Fill holes and cracks with a suitable filling compound, block down, sand to an even finish, dust off. On bare areas treat as for new work.

Application Details	Data Sheet	Coverage m ² /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: Taubmans UnderProof All Purpose Undercoat (equipment: brush, roller or spray)	TA004	8-14	71-125	39-68	30 minutes	2 hours
Second Coat: Taubmans LivingProof Eggshell / Satin / Silk (equipment: brush, roller or spray)	TA040-42	14-16	62-71	25-29	30 minutes	2 hours
Third Coat: Taubmans LivingProof Eggshell / Satin / Silk (equipment: brush, roller or spray)	TA040-42	14-16	62-71	25-29	30 minutes	2 hours

Recommended Uses For interior use only.
Suitable for use on correctly prepared brick, cement, stone, paperfaced plasterboard and previously painted surfaces. Ideal for domestic passageways and other high usage living areas.

Additional Notes Leave seven days after application of final coat before washing.
When subject to steam or condensation, water based paints may develop a stain, which can be removed with a damp cloth. Avoid exposure to excessive steam or condensation for 48 hours after application of the final coat.

Caution Provide adequate ventilation during use.
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

- This information is provided with respect to the listed Wattyl products. Wattyl recommends that:
 - you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product;
 - the product be used only in accordance with the information provided by Wattyl;
 - the product be transported, stored and handled in accordance with the information on the (MSDS) and relevant TDS; and
 - you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
- Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.
- To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.