

# Paintworks Specification NZ 030.2

**System** Taubmans Gaylon Satin Enamel

**Substrate** Interior - Previously painted interior water based / acrylic finishes

**Category** Premium – Turps Based Enamel

**Product Features**

Taubmans Gaylon Satin Enamel is a high quality, hard wearing satin enamel finish, which resists abrasion and protects interior surfaces. Taubmans Gaylon Satin Enamel offers outstanding durability and washability.

**Surface Preparation. Refer to section 4 of the Watty Specifiers Manual**

Minimum Surface Preparation. Ensure the surface is clean and dry. All loose, peeling and flaking material must be removed with a scraper. Fill holes and cracks with a suitable filling compound, block down, sand to an even finish, dust off. On bare areas treat as for new work.

Application Details	Data Sheet	Coverage m <sup>2</sup> /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: <b>Taubmans UnderProof Primer Sealer Undercoat</b> <i>(equipment: brush, roller or spray)</i>	TA011	8-14	71 to 125	27-47	30 mins	2 hours
Second Coat: <b>Taubmans Gaylon Satin Enamel</b> <i>(equipment: brush, roller or spray)</i>	TA051	14-16	63-71	28-32	4 hours	24 hours
Third Coat: <b>Taubmans Gaylon Satin Enamel</b> <i>(equipment: brush, roller or spray)</i>	TA051	14-16	63-71	28-32	4 hours	24 hours

**Recommended Uses** For interior use only.  
For use on suitably prepared timber, plaster, cement, fibre cement, paperfaced plasterboard, galvanised iron, bare steel and previously painted surfaces.

**Additional Notes** Leave seven days after application of final coat before washing.  
Avoid using household cleaners containing high levels of ammonia for a period of two weeks after application of the enamel.

**Caution** Provide adequate ventilation during use.  
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Watty products. Watty recommends that:  
(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the (MSDS) and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.  
2. The information in this technical data sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.  
3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Watty Office.  
4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.