

Paintworks Specification NZ 080.1

System Taubmans Easyflo Quick Dry Gloss Enamel

Substrate Interior - Previously painted interior oil based/enamel finishes

Category Trade Premium – Turps Based Enamel

Product Features

Taubmans Easyflo Quick Dry Gloss Enamel is a high quality, hard wearing gloss finish with outstanding durability and wash-ability. This product flows out to give a smooth even surface.

Surface Preparation. Refer to section 4 of the Wattyl Specifiers Manual

Minimum Surface Preparation. Ensure the surface is clean and dry. All loose, peeling and flaking material must be removed with a scraper. Remove all gloss on painted surfaces with 220 abrasive paper. Fill holes and cracks with a suitable filling compound, block down, sand to an even finish, dust off. On bare areas treat as for new work.

Application Details	Data Sheet	Coverage m ² /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: Taubmans Tradex Oil Based Undercoat (equipment: brush, roller or spray)	TA072	8-14	71-125	39-68	4 hours	16 hours
Second Coat: Taubmans Easyflo Quick Dry Gloss Enamel (equipment: brush, roller or spray)	TA055	14-16	63-71	28-32	2 hours	6 hours
Third Coat: Taubmans Easyflo Quick Dry Gloss Enamel (equipment: brush, roller or spray)	TA055	14-16	63-71	28-32	2 hours	6 hours

Recommended Uses For interior use only.
For use on suitably prepared timber, plaster, cement render, paperfaced plasterboard, galvanised iron, bare steel and previously painted surfaces.

Additional Notes Excess film thickness will result in runs and slow drying
Leave seven days after application of final coat before washing.

Caution Provide adequate ventilation during use.
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheet (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the (MSDS) and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.

4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.