

# Paintworks Specification NZ 221.1

**System** Taubmans Weatherglo 100% Acrylic Low Lustre

**Substrate** Exterior - Previously painted exterior oil based/enamel finishes

**Category** Trade Premium – Water Based

## Product Features

Taubmans Weatherglo 100% Acrylic Low Lustre is a premium quality, water based, 100% acrylic paint with excellent exterior durability

## Surface Preparation - Refer to section 4 of the Wattyl Specifiers Manual

Minimum surface preparation. Ensure the surface is clean and dry. All loose, peeling and flaking material must be removed with a scraper. Remove all gloss on painted surfaces with 220 abrasive paper. Fill holes and cracks with a suitable filling compound, block down, sand to an even finish, dust off. On bare areas treat as for new work.

Application Details	Data Sheet	Coverage m <sup>2</sup> /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: <b>Taubmans Weatherglo 100% Acrylic Low Lustre</b> (equipment: brush, roller or spray)	TA029	8-16	63-125	26-52	30 minutes	2 hours
Second Coat: <b>Taubmans Weatherglo 100% Acrylic Low Lustre</b> (equipment: brush, roller or spray)	TA029	8-16	63-125	26-52	30 minutes	2 hours

**Recommended Uses** For exterior use only.  
For use on suitably prepared exterior timber, all masonry, brick, # fibre cement sheets, cement render, tilt-up and pre-cast panels, galvanised iron, bare steel, PVC (downpipes) and previously painted surfaces.

**Additional Notes** Ensure the previously painted surface is in sound condition. To test, cut a small X through the paint with a sharp blade. Apply a piece of adhesive tape over the X and rip off. If the paint peels away, the surface is unsound. Unsound areas should be stripped or sanded back to bare.  
# Excludes all monolithic (where joints are taped and set) fibre cement sheets for exterior use. Refer to the Granosite Texture Solutions Specification Manual for the recommended coating systems for these sheet systems.

**Caution** Provide adequate ventilation during use.  
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

- This information is provided with respect to the listed Wattyl products. Wattyl recommends that:
  - you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product;
  - the product be used only in accordance with the information provided by Wattyl;
  - the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and
  - you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.
- Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Wattyl Office.
- To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.