

Paintworks Specification NZ 225.1

System Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel

Substrate Exterior - Previously painted exterior oil based/enamel finishes

Category Premium – Water Based Acrylic Enamel

Product Features

Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel is an advanced formulation acrylic with enamel-like characteristics for interior and exterior use. It combines the smooth finishing properties and serviceability of enamels with the low odour, quick dry, and convenience of water based finishes.

Surface Preparation. Refer to section 4 of the Watty! Specifiers Manual

Minimum Surface Preparation. Ensure the surface is clean and dry. All loose, peeling and flaking material must be removed with a scraper. Remove all gloss on painted surfaces with 220 abrasive paper. Fill holes and cracks with a suitable filling compound, block down, sand to an even finish, dust off. On bare areas treat as for new work.

Application Details	Data Sheet	Coverage m ² /L	Film Thickness (microns)		Dry Times (minimum)	
			Wet	Dry	Touch	Recoat
First Coat: Taubmans UnderProof Acrylic Primer Undercoat <i>(equipment: brush, roller or spray)</i>	TA002	8-14	71-125	28-49	30 minutes	2 hours
Second Coat: Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel <i>(equipment: brush, roller or spray)</i>	TA047-49	14-16	63-71	23-26	30 minutes	4 hours
Third Coat: Taubmans UltraProof Gloss /Satin / Semi Gloss Acrylic Enamel <i>(equipment: brush, roller or spray)</i>	TA047-49	14-16	63-71	23-26	30 minutes	4 hours

Recommended Uses For interior and exterior use.
Suitable for use on suitably prepared timber Doors, Windows and Trim.

Additional Notes **Note:** Not recommended for exterior weather boards.

Caution Provide adequate ventilation during use.
Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Watty! products. Watty! recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty!; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
2. The information in this technical data sheet was prepared using information gathered during product development. While Watty! endeavours to update this information and maintain the accuracy and currency of its contents, Watty! cannot guarantee that the information provided is wholly comprehensive.
3. Watty! recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If this datasheet is greater than 3 years old at the time of reading, or if you require further information please contact your nearest Watty! Office.
4. To the full extent permitted by law, Watty!'s liability for breach of a condition or warranty implied into the contract for sale between Watty! and you by law is limited at Watty!'s election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.