

# Paintworks Specification GS 106.1NZ

|                  |  |
|------------------|--|
| <b>System</b>    | GranoClassic® Spray Membrane                                       |
| <b>Substrate</b> | Exterior – Previously painted oil based / enamel exterior surfaces |
| <b>Category</b>  | Premium Texture – Water Based                                      |

## Product Features

GranoClassic® is a spray applied pigmented acrylic texture coating giving an elegant yet traditional stone-like finish.

## Surface Preparation

Remove all paint, which is soft, blistered, loose, or flaking back to a firm edge. Areas where the previous coatings were powdery, remove all powder. Wash all surfaces with mild detergent to remove contaminants, rinse with clean water. Remove all gloss on painted surfaces with 220 abrasive paper. Fill any cracks, holes or imperfections with GranoPatch® Smooth (G1.04NZ), allow to dry, sand back and dust off.

| Application Details   | Data Sheet | Coverage                | Film Thickness (microns) |     | Dry Times |          |
|---|------------|-------------------------|--------------------------|-----|-----------|----------|
|   |            |                         | Wet                      | Dry | Touch     | Topcoat  |
| First Coat:<br><b>UnderProof All Purpose Undercoat</b><br><i>(equipment: brush, roller or spray)</i>                        | TA004      | 0.07 L/M <sup>2</sup>   | 75                       | 39  | 4 hours   | 24 hours |
| Second Coat:<br><b>GranoClassic®</b><br><i>(equipment: hopper spray gun)</i>  | G2.08NZ    | 2.00 Kg/ M <sup>2</sup> | 1020                     | 670 | 4 hours   | 24 hours |
| Third & Fourth Coat:<br><b>GranoSkin® Membrane</b><br><i>(equipment: roller, for spray application refer the datasheet)</i> | G2.14NZ    | 0.12 L/M <sup>2</sup>   | 125                      | 62  | 4 hours   | 6 hours  |

## Recommended Uses

For exterior or interior use.

For use on suitably prepared off-form concrete Class 2 (AS 1510) or equivalent, cement rendered fair-faced flush-jointed concrete block and brickwork (common, clay, concrete), tilt-up and pre-cast concrete, Autoclaved Aerated Concrete (AAC), CFC, fibre cement sheet and polystyrene sheets. See the appropriate system specification sheet for further details.

## Additional Notes

Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations.

It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty's Granosite products and systems, to validate full material warranty conditions.

## Caution

Provide adequate ventilation during use.

Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.

1. This information is provided with respect to the listed Watty products. Watty recommends that:

(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Watty; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this specification sheet was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty cannot guarantee that the information provided is wholly comprehensive.

3. Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty Office.

4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.