

Paintworks Specification GS 121.4NZ

System	GranoImpact® Low Profile
Substrate	Exterior – Rejuvenate existing texture
Category	Premium Texture – Water Based

Product Features

GranoImpact® is a pure acrylic, high performance elastomeric coating able to be applied in a variety of styles by roller or spray. Approved to APAS 0118/2 & APAS 0117/3.

Surface Preparation

Remove all coating, which is blistered, loose, or flaking back to a firm edge. This can be achieved through high-pressure water cleaning at 500-1000psi. Allow to dry.

Repair or replace texture to match existing where required. Allow to dry.

Two (2) coat system: Apply one (1) coat of GranoBasecoat® (G1.11NZ). Allow to dry. Apply one (1) coat GranoImpact® (G2.01NZ) or both coats to be tinted to desired colour.

Three (3) coat system: Apply one (1) coat of GranoPrime® (G1.02NZ) undiluted. Allow to dry. Apply two (2) coats GranoImpact® (G2.01NZ).

Note GranoSkin® Membrane (G2.14NZ) must be used when rejuvenating Autoclaved Aerated Concrete (AAC) blocks or panels, Fibre Cement Sheets, Polystyrene systems.

Application Details	Data Sheet	Coverage	Film Thickness (microns)		Dry Times	
			Wet	Dry	Touch	Topcoat
First Coat: GranoPrime® (equipment: roller or spray)	G1.02NZ	0.08 L/M ²	80	20	2 hours	6 hours
Second Coat: GranoImpact® (equipment: 10 – 12mm pile roller)	G2.01NZ	0.18 L/M ²	150	70	4 hours	6 hours
Third Coat: GranoImpact® (equipment: 10 – 12mm pile roller)	G2.01NZ	0.18 L/M ²	150	70	4 hours	6 hours

Recommended Uses	For exterior or interior use. For use on suitably prepared off-form concrete Class 2 (AS 1510) or equivalent, cement rendered fair-faced flush-jointed concrete block and brickwork (common, clay, concrete), CFC, tilt-up and pre-cast concrete. See the appropriate system specification sheet for further details.
-------------------------	--

Additional Notes	Surface preparation is the responsibility of the Builder, Renovator or Main Contractor and the Applicator. To achieve the indicated performance, it must be carried out according to Watty's recommendations. It is recommended that application be carried out by a skilled applicator, who is totally conversant with the Watty's GranoSite products and systems, to validate full material warranty conditions.
-------------------------	---

Caution	Provide adequate ventilation during use. Application should not be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.
----------------	---

- This information is provided with respect to the listed Watty's products. Watty's recommends that:
 - you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product;
 - the product be used only in accordance with the information provided by Watty's;
 - the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and
 - you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
- The information in this specification sheet was prepared using information gathered during product development. While Watty's endeavours to update this information and maintain the accuracy and currency of its contents, Watty's cannot guarantee that the information provided is wholly comprehensive.
- Watty's recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty's Office.
- To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty's and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.