

## Wattyl Killrust Rust Eater (Rust converter)

### PRODUCT DESCRIPTION

A specially formulated rust converter for iron and steel surfaces that are badly corroded. It reacts with rust to reduce corrosion and provide a superior bond for primers and paints

### INTENDED USES – INTERIOR/EXTERIOR

- All badly rusted metal surfaces
- Rusted steel or wrought iron

### TECHNICAL DATA

- Vehicle Type Specialty resin system
- Pigmentation Not applicable
- Solvent Hydrocarbon
- Pot Life Not applicable
- Finish Not applicable
- Colour Clear liquid, black when dry
- Touch Dry Time 30 minutes at 20°C and 65% RH
- Recoat Time 24 hours at 20°C and 65% RH
- Preparatory Coat Not applicable
- Theoretical Coverage 8 – 14m<sup>2</sup>/L depending on porosity and texture of the surface
- Dry Film Thickness 15 – 25µ
- Usual Number of Coats 1
- Toxicity Corrosive – avoid skin and eye contact
- Durability Must be primed
- Thinning and Clean Up Wattyl Spraying Thinners
- V.O.C. >300g/L as per EC-07-01
- Pack Sizes 500mL

## PERFORMANCE PARAMETERS

### Features

- Designed especially to stop corrosion and provide a superior bonding surface for paints.

### Constraints

- Do not apply when temperature is below 10°, the humidity is greater than 85% or if dew or rainfall is likely within 4 hours of application.
- Prime within 4 weeks.
- Not suitable for use on galvanized iron or under lacquers or two pack finishes.

## SURFACE PREPARATION

Any loose rust or peeling, flaking paint must be removed by wire brushing or mechanical sanding. Remove grease, oil, dust and dirt by washing with a degreaser and/or a detergent. Rinse thoroughly with clean fresh water and allow to dry.

## APPLICATION

Apply one coat of Wattyl Killrust Rust-Eeter by brushing, dipping or spraying. For best results, prime with Wattyl Killrust Metal Primer and overcoat with Wattyl Killrust Superior Protection Epoxy Enamel.

Do not overcoat with a lacquer or two pack product

Do not overcoat with a water based product, use Wattyl Killrust Metal Primer first.

## NOTES

### Warning:

Killrust Rust-Eeter is not intended as a heavy duty coating primer.

### Safety directions:

Avoid contact with skin and eyes. Wear goggles and rubber gloves during use.

### First Aid:

If poisoning occurs, contact a doctor or Poisons Information Centre. If swallowed DO NOT induce vomiting. Give a glass of water and seek medical attention immediately. If skin contact occurs remove contaminated clothing and wash skin thoroughly. If in eyes, hold eye lid open and flush with water for 15 minutes. Seek medical attention immediately.



Wattyl Killrust Rust-Eeter forms part of the comprehensive Wattyl Killrust metal protection and decoration range. For maximum protection it should be used in conjunction with other components selected from this range.

## MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

NOTE: The information concerning the use and application of these products is intended for use by professional specifiers and is believed to be correct at the date of printing, and is given in good faith. Wattyl (NZ) Ltd reserves the right to alter the product or specification without notice. The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)