

Wattyl Killrust Oil Based Galvanised Iron Primer

PRODUCT DESCRIPTION

An oil based, high performance corrosion inhibiting primer for use on new and weathered galvanised iron and mild steel. It provides protection against white rusting and has excellent adhesion properties.

INTENDED USES – INTERIOR/EXTERIOR

- New or weathered galvanised iron
- Painted galvanised iron surfaces

TECHNICAL DATA

- Vehicle Type Alkyd
- Pigmentation Titanium dioxide, extenders and corrosion inhibitors
- Solvent Mineral Turpentine
- Pot Life Not applicable
- Finish Flat
- Colour Grey
- Touch Dry Time 4 hours at 20°C and 65% RH
- Recoat Time 24 hours at 20°C and 65% RH
- Preparatory Coat Not applicable
- Theoretical Coverage 12 – 14m²/L depending on porosity and texture of the surface
- Dry Film Thickness 35 – 45µ
- Usual Number of Coats 1
- Toxicity of dry film Non Toxic
- Durability Must be top coated
- Thinning and Clean Up Mineral Turpentine
- V.O.C. >300g/L as per EC-07-07
- Pack Sizes 500mL, 1L, 4L

PERFORMANCE PARAMETERS

Features

- Safe for use on roofs used for the collection of drinking water.
- Prevents corrosion.
- Promotes adhesion of subsequent coats.

Constraints

- Do not apply when the temperature is below 10°C, the humidity is greater than 85%, or if dew or rainfall is likely within 4 hours of application.
- Lower temperatures, high humidity and poor ventilation will prolong drying times.
- On rusted galvanised iron surfaces that cannot be adequately cleaned we recommend Wattyl Killrust Fishoilene as the priming coat prior to Wattyl Killrust Oil Based Galvanised Iron Primer.

SURFACE PREPARATION

The surface to be coated must be clean, dry and free from wax, grease, dust and any loose or flaking paint. Degrease new galvanised iron with Wattyl Roof Wash as per label instructions. White zinc salts, if present, must be removed by scrubbing with Wattyl Roof Wash and water, rinsed with clean water and allowed to dry. Any areas of red rust must be wire brushed to clean metal. Cleaned surfaces should be primed within 4 hours to prevent rust from recurring.

APPLICATION

Stir thoroughly with a flat stick before and occasionally during use.
Wattyl Killrust Oil Based Galvanised Iron Primer may be applied by brush, roller or spray.

NOTES



Wattyl Killrust Oil Based Galvanised Iron Primer is safe for use on roofs used for the collection of drinking water. To prevent possible tainting, we recommend the tank pipe be disconnected prior to preparation and reconnected after the first HEAVY rainfall once painting is complete.
Wattyl Killrust Oil Based Galvanised Iron Primer forms part of the comprehensive Wattyl Killrust metal protection and decoration range. For maximum protection it should be used in conjunction with other components selected from this range.

MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

NOTE: The information concerning the use and application of these products is intended for use by professional specifiers and is believed to be correct at the date of printing, and is given in good faith. Wattyl (NZ) Ltd reserves the right to alter the product or specification without notice. The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)