

Wattyl Flexigard Primer

PRODUCT DESCRIPTION

An acrylic primer especially for cementitious surfaces. Intended for use under Wattyl Flexigard Low Sheen.

INTENDED USES – INTERIOR/EXTERIOR

- Fibre cement
- Concrete block
- Stucco plaster

TECHNICAL DATA

- | | |
|-------------------------|---|
| • Vehicle Type | Cement Compatible Acrylic |
| • Pigmentation | Titanium dioxide |
| • Solvent | Water |
| • Pot Life | Not applicable |
| • Finish | Flat |
| • Colour | White, cannot be tinted |
| • Touch Dry Time | 30 minutes at 20°C and 65% RH |
| • Recoat Time | 2 hours at 20°C and 65% RH |
| • Preparatory Coat | Not applicable |
| • Theoretical Coverage | 12 – 14m ² /L depending on porosity and texture of the surface |
| • Dry Film Thickness | 40µ |
| • Usual Number of Coats | 1 |
| • Toxicity of dry film | Non Toxic |
| • Durability | Must be top coated |
| • Thinning and Clean Up | Clean Water |
| • V.O.C. | 29 g/L as per EC-07-07 |
| • Pack Sizes | 4L, 10L |

PERFORMANCE PARAMETERS

Features

- It binds and controls porosity producing a surface of uniform density for top coating.
- Key coat for old or painted cementitious surfaces.

Constraints

- Do not apply when the temperature is below 10°C, the humidity is greater than 85%, or if dew or rainfall is likely within 4 hours of application.
- On off-form or tilt slab concrete use Taubmans Tradex Tilt Slab Sealer
- Not intended for walk on surfaces.

SURFACE PREPARATION

Fresh concrete and plastered surfaces must be allowed to cure before painting, typically 28 days for poured concrete, or as recommended by the plaster manufacturer.

For sprayed plasters ensure surfaces are clean, sound and free from salts, efflorescence, dirt and loose cement dust.

On poured concrete and tilt slab construction, mould release agents must be removed by detergent washing and the surface should show no trace of water repellency before proceeding.

All surfaces must be clean, dry and sound before this product is applied.

APPLICATION

Thin Wattyl Flexigard Primer with an equal volume of water. Stir thoroughly with a flat stick before and occasionally during use. Apply by long nap roller or brush till the surface is saturated. Allow to dry.

NOTES

Spraying is not recommended, as it does not work the material into the surface.

Primed surfaces should be top coated without delay to prevent surface contamination.



Overcoat the primer within 7 days.

MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

NOTE: The information concerning the use and application of these products is intended for use by professional specifiers and is believed to be correct at the date of printing, and is given in good faith. Wattyl (NZ) Ltd reserves the right to alter the product or specification without notice. The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)