

Wattyl Roofgard Basecoat Additive

PRODUCT DESCRIPTION

A flexible and binding additive for use in the initial coat of Wattyl Roofgard Basecoat when refurbishing stone chip coated roofs

INTENDED USES – EXTERIOR

- Stone chip coated roofs

TECHNICAL DATA

- | | |
|-------------------------|-------------------------|
| • Vehicle Type | Water dispersed polymer |
| • Pigmentation | Not applicable |
| • Solvent | Water |
| • Pot Life | Not applicable |
| • Finish | Not applicable |
| • Colour | Not applicable |
| • Touch Dry Time | Not applicable |
| • Recoat Time | Not applicable |
| • Preparatory Coat | Not applicable |
| • Theoretical Coverage | Not applicable |
| • Dry Film Thickness | Not applicable |
| • Usual Number of Coats | Not applicable |
| • Toxicity of dry film | Non Toxic |
| • Durability | Not applicable |
| • Thinning and Clean Up | Clean Water |
| • V.O.C. | <1g/L as per EC-07-07 |
| • Pack Sizes | 1L |

PERFORMANCE PARAMETERS

Features

- Improves the adhesion and stone chip binding of Wattyl Roofgard Basecoat

Constraints

- Do not apply when the temperature is below 10°C, the humidity is greater than 85%, or if dew or rainfall is likely within 4 hours of application.
- Recommended for use by Trade Painters only

SURFACE PREPARATION

Clean all surfaces with Wattyl Antimould Pre-Wash, followed by low pressure washing. Areas of rust are to be wire brushed and primed with Wattyl Killrust Cold Galvit. Bare areas to be primed with Roofgard Acrylic Galvanized Iron Primer.

APPLICATION

Mix 1 litre Wattyl Roofgard Basecoat Additive into 15 litres Wattyl Roofgard Basecoat by stirring with a power drill. Stir thoroughly with a flat stick before and during use.

Spray a coat of the mixed Wattyl Roofgard Basecoat and Additive by airless spray, typical set up pressure 2200 – 2700psi, 17thou tip, at 5m²/L. Sprinkle stone chips in the wet paint. Spray another coat over the freshly chipped areas at 5m²/L. Allow to dry for at least 2 hours.

Apply one coat of Wattyl Roofgard Basecoat without additive at 2.5m²/L to the entire surface.

NOTES

Wattyl Roofgard Basecoat with additive may be stored indefinitely.



Do not apply to wet surfaces. Avoid painting if the roof temperature is above 30°C.

MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

NOTE: The information concerning the use and application of these products is intended for use by professional specifiers and is believed to be correct at the date of printing, and is given in good faith. Wattyl (NZ) Ltd reserves the right to alter the product or specification without notice. The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)