

# KILLRUST HAMMERED METAL FINISH

## PRODUCT DESCRIPTION

Wattyl Killrust Hammered Metal Finish provides a distinctive coating that resembles hammered sheet metal.

## INTENDED USES – INTERIOR/EXTERIOR

- For finishing sheet metal work, castings, office equipment and machinery where a decorative effect is required
- Can be used on other substrates with suitable priming

## TECHNICAL DATA

- Vehicle Type Alkyd
- Pigmentation Oxides and organic pigments
- Solvent Mineral Turpentine
- Pot Life Not applicable
- Finish Gloss
- Colour Refer to Wattyl KILLRUST Colour Card
- Touch Dry Time 30 minutes at 20°C and 65% RH.
- Recoat Time Between 1-8 hours at 20°C and 65% RH. Allow up to twice as long for cooler and more humid conditions.
- Preparatory Coat Required
- Theoretical Coverage 2m<sup>2</sup> /300g aerosol (depending on the texture and surface porosity).
- Dry Film Thickness N/A
- Usual Number of Coats 2
- Toxicity of dried film Non toxic
- Durability Good
- Thinning and Clean Up Thinning not required. Thoroughly clean equipment with mineral turpentine.
- V.O.C. >300mg/L as per EC-07-07
- Pack Sizes 300g Aerosol

## PERFORMANCE PARAMETERS

### Features

- Provides a distinctive coating that resembles hammered sheet metal.
- Ideal for camouflaging imperfect metal surfaces, hiding scratches and weld joints.

### Constraints

- Application should not be carried out if the air temperature of the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.
- Do not overcoat or touch up KILLRUST HAMMERED METAL FINISH with products other than itself.
- Completely remove KILLRUST HAMMERED METAL FINISH prior to repainting with a non hammered paint.

## SURFACE PREPARATION

**Aluminium Surfaces:** New/unpainted The surface to be coated must be clean, dry and free from wax, grease, dust and any loose or flaking paint. Remove all rust and any loose or flaking paint by wire brush, disc grinding or abrasive blast cleaning, to give a clean, bright surface. Lightly scuff the surface to aid adhesion. Apply 1 coat of KILLRUST SUPER ETCH PRIMER.

**Steel or Wrought Iron Surfaces:** New/unpainted: The surface to be coated must be clean, dry and free from wax, grease, dust and any loose or flaking paint. Remove all rust and any loose or flaking paint by wire brush, disc grinding or abrasive blast cleaning, to give a clean, bright surface. Cleaned surfaces should be primed within 4 hours to prevent rust from recurring.

Light rust may be removed with Wattyl Killrust Metal-Prep to enhance corrosion resistance and paint adhesion. Apply 1 coat of KILLRUST METAL PRIMER.

For other surfaces contact the Wattyl Help Line: 0800735 551

## APPLICATION

Shake can for a full minute before use and time to time during use. Keep can about 25cm from the surface at all times.

Keep the spray moving to and fro with smooth strokes, ensuring the area has been completely coated.

Spray two or more mist coats wet on wet, rather than one heavy coat, which may run.

## NOTES

Provide adequate ventilation during use.

Wattyl Hammered Metal Finish forms part of the comprehensive Wattyl Killrust metal protection and decoration range. For maximum protection it should be used in conjunction with other components selected from this range.

Contains silicone, mask all areas to avoid silicone contamination.

## MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z.) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:




(a) The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. (b) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (c) the product be used only in accordance with the information provided by Wattyl; (d) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (e) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.

4. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)