

Wattyl Forestwood Decking Stain

PRODUCT DESCRIPTION

A see through, oil fortified stain for exterior timber decks, verandas and pergolas in new or good condition. Wattyl Forestwood Decking Stain adds natural colour whilst penetrating the timber to preserve and protect. Ideal for use on durable softwoods and close grained hardwoods used for decking and related applications. Available in a range of pre-mixed factory colours. Wattyl Forestwood Decking Stain enhances the natural beauty of the timber, allowing the grain pattern to show through. It must be regarded as a maintainable coating with less life expectancy than opaque paint. For a longer life, solid cover, water based finish for new. Older or weathered timbers use Taubmans TimberProof Low Sheen Acrylic.

INTENDED USES – EXTERIOR

- Timber decks
- Verandahs, pergolas

TECHNICAL DATA

- | | |
|-------------------------|--|
| • Vehicle Type | Modified Oil |
| • Pigmentation | Oxide Pigments |
| • Solvent | Mineral Turpentine |
| • Pot Life | Not applicable |
| • Finish | Matt oiled look |
| • Colour | Available in a range of standard colours |
| • Touch Dry Time | Being oil based may take up to several days to fully harden |
| • Recoat Time | 24 hours (minimum) |
| • Preparatory Coat | Not required |
| • Theoretical Coverage | 4 -12 m ² /L depending on porosity and texture of the surface |
| • Dry Film Thickness | Not applicable |
| • Usual Number of Coats | 2 |
| • Toxicity of dry film | Non Toxic |
| • Durability | Good |
| • Thinning and Clean Up | Mineral turpentine |
| • V.O.C. | >300g/L as per EC-07-07 |
| • Pack Sizes | 1L, 5L,10L |

PERFORMANCE PARAMETERS

Features

- The oil fortified formula penetrates the timber and provides colour, whilst preserving and protecting the finish.
- Protects timber from U.V degradation.

Constraints

- Do not apply when the temperature is below 10°C, the humidity is greater than 85% or if dew or rainfall is likely within 4 hours of application.
- Not suitable for used over surfaces previously primed or coated with paint type finishes.
- New Kwila decking should be allowed to weather for at 2 to 3 months prior to staining

SURFACE PREPARATION

Ensure surface is in good condition. Remove any grease, dust, dirt, mildew, wax etc. Galvanised nails should be used to avoid rust stains.

Mould – Remove as much mould growth as possible by scraping and stiff brushing. Apply a mixture of 1L hypochlorite bleach, 20mls liquid sugar soap in 3 litres of water by spray or brush. Leave for 30 minutes then hose off and allow the surface to dry. Alternatively a proprietary fungicidal wash may be used as directed.

APPLICATION

Stir thoroughly before use and regularly during use with a broad, flat stirrer. Apply using a good quality brush.

Bare Timber: Brush a generous coat well into the timber. One coat gives satisfactory coverage to most timbers. A second coat will give longer lasting protection in positions exposed to strong sunlight. Wiping off is not required. Allow 24 hours before recoating.

NOTES

Wattyl Forestwood Decking Stain is not suitable for areas subject to car traffic or parking. Not suitable for use on any non timber surface.

Caution: Wattyl Forestwood Decking Stain should only be used over bare timber or similar oil based stain finishes. Not suitable for interior use.



Maintenance: Re-staining should be conducted every 2-3 summers, or as soon as the timber shows signs of weathering due to exposure. If the timber retains sufficient depth of colour select a light stain such as Rustic Oak for rejuvenation. Clean surfaces as outlined above before re-staining.

MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

NOTE: The information concerning the use and application of these products is intended for use by professional specifiers and is believed to be correct at the date of printing, and is given in good faith. Wattyl (NZ) Ltd reserves the right to alter the product or specification without notice. The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)