

Wattyl Colourwood Wood Gel

PRODUCT DESCRIPTION

Wattyl Colourwood Wood Gel is a water based semi transparent easy to use gel formula pigmented wiping stain. It has good clarity and is suitable for use on all timber types. In conjunction with Wattyl Estapol Speed Clear it gives a rapid finishing system option that is totally water based.

INTENDED USES – INTERIOR

- Furniture
- Wall paneling
- Timber joinery
- Wooden toys
- Doors etc.

TECHNICAL DATA

- | | |
|-------------------------|---|
| • Vehicle Type | Acrylic |
| • Pigmentation | Oxide pigmentation and fillers |
| • Solvent | Water |
| • Pot Life | Not applicable |
| • Finish | Not applicable |
| • Colour | Available in a range of timber tones, refer to colour chart |
| • Touch Dry Time | 1 hour at 20°C and 65% RH |
| • Recoat Time | 4 hours at 20°C and 65% RH. Allow up to twice as long for cooler and more humid conditions. |
| • Preparatory Coat | Not required |
| • Theoretical Coverage | Not Applicable |
| • Dry Film Thickness | Not Applicable |
| • Usual Number of Coats | 1 |
| • Toxicity of dry film | Non Toxic |
| • Durability | Top coat recommended |
| • Thinning and Clean Up | Clean Water |
| • V.O.C. | 125g/L as per EC-07-07 |
| • Pack Sizes | 200mL tube |



PERFORMANCE PARAMETERS

Features

- Low odour and rapid dry.
- Especially suited to pine and white wood furniture which may give patchy results with dye type stains.
- Adds colour to timber without hiding the natural grain.

Constraints

- Not suitable for use on floors.
- Some timbers particularly natives such as Rimu, Totara and Matai are best sealed after staining with Wattyl Estapol Speed Clear to prevent slow drying that might occur if a turpentine based polyurethane was used.
- Wattyl Colourwood Wood Gel is not a finish by itself and requires clear coating to provide protection, true colour and gloss.

SURFACE PREPARATION

Bare Timber: Ensure the surface to be coated is thoroughly dry, and free from dirt, grease and wax. Fill all nail holes and small cracks in timber sparingly with Wattyl Colourwood Timber Putty, in a matching timber colour, and allow to dry for at least 30 minutes. Sand along the grain with fine sandpaper, to a very smooth surface. Thoroughly remove all dust with a cloth dampened with water.

Previously Painted Surfaces: Completely strip the surface with Wattyl Stripaway, and wash down to remove all residue. Sand clean before staining, and thoroughly remove all dust with a cloth dampened with water.

APPLICATION

Squeeze Wattyl Colourwood Wood Gel onto an applicator (clean cloth, speed brush etc) and apply to the timber. Apply liberally rubbing in a circular motion. Allow to stand for 1-3 minutes before removing the excess by vigorously wiping along the grain with a clean cloth. One coat is only required. Always test the colour on an off-cut piece of wood or out of sight area.

If colour is too dark it may be diluted with water. On large areas dampening the surface with water may be of assistance in ensuring the stain does not dry before the excess is removed

NOTES

Do not overcoat with Wattyl Estapol Moisture Cured Polyurethane.

MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:



(a) The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. (b) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (c) the product be used only in accordance with the information provided by Wattyl; (d) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (e) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.

4. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)