

Wattyl Estapol Slate and Pebble Clear

PRODUCT DESCRIPTION

Wattyl Estapol Slate and Pebble Clear provides a tough protective coating for a range of interior and exterior surfaces. It will help resist penetration from spillages such as oil, grease and food. It is suitable for application to surfaces subject to domestic foot traffic. It helps bind exposed aggregate and pebblecrete while strengthening masonry surfaces against eroding and dusting. Wattyl Estapol Slate and Pebble Clear will not yellow over time.

INTENDED USES – INTERIOR/EXTERIOR

- Exposed aggregate, slate
- Pebble finishes
- Concrete (including stamped)
- Clay pavers, unglazed quarry tiles
- Brick
- Sandstone

TECHNICAL DATA

- | | |
|-------------------------|--|
| • Vehicle Type | Solution Acrylic |
| • Pigmentation | Not Applicable |
| • Solvent | Hydrocarbon |
| • Pot Life | Not applicable |
| • Finish | Gloss |
| • Colour | Clear |
| • Touch Dry Time | 1 hour at 20°C and 65% RH |
| • Recoat Time | 3 hours at 20°C and 65% RH |
| • Preparatory Coat | Not required |
| • Theoretical Coverage | 10 -14m ² /L depending on porosity and texture of substrate |
| • Dry Film Thickness | 20µ |
| • Usual Number of Coats | 1 - 2 |
| • Toxicity of dry film | Non Toxic |
| • Durability | Good |
| • Thinning and Clean Up | Wattyl Estapol Slate and Pebble Reducer |
| • V.O.C. | >300 g/L as per EC-07-01 |
| • Pack Sizes | 1L, 4L |

PERFORMANCE PARAMETERS

Features

- Will help strengthen masonry surfaces against eroding and dusting.
- Non-yellowing, and can withstand normal domestic traffic.
- Ideal for use on bathroom, kitchen and laundry floors, foyers, verandahs and courtyards.

Constraints

- Produces a smooth surface that may be slippery when wet, apply with caution in these areas.

SURFACE PREPARATION

Before application, ensure the surface is thoroughly dry and free from dirt, grease, wax, efflorescence (white salts) or any loose flaking material.

If mould is present treat with mould killer diluted 4:1 in water. Brush on, leave 30 minutes, rinse off and allow to dry otherwise wash the surface with warm water and household detergent.

If necessary ensure removal of any grease, oil, wax or polish with Mineral Turpentine. If the existing coating is unsound, remove the previous coating with Wattyl Stripaway or Wattyl Estapol Slate and Pebble Clear Reducer prior to recoating.

New concrete surfaces should be left to fully cure for approximately 4 - 6 weeks. All cracks or damaged areas should be repaired prior to application.

Smooth trowelled concrete surfaces should be acid etched to ensure maximum adhesion of coating. Allow new grouting to dry for at least 2 weeks prior to finishing.

APPLICATION

Stir contents thoroughly before use. Apply using a brush or roller (a wool roller is recommended). A single coat will give satisfactory coverage on most surfaces. For areas subject to heavy foot traffic, or on very porous surfaces a second coat is recommended. For improved adhesion on porous surfaces, such as slate and unglazed quarry tiles, thin the first coat up to 30% with Wattyl Estapol Slate and Pebble Clear Reducer. Apply a second coat unthinned.

NOTES

Not suitable for use on glazed quarry tiles, rubber, vinyl, linoleum, areas exposed to salt water, timber or bitumen. Not recommended for areas exposed to direct flame or extreme heat (e.g. barbeque and fireplace surrounds). Not recommended for drive on surfaces e.g. garage floors or driveways.

Maintenance: Proper maintenance will prolong the life of the finish. Do not apply Wattyl Estapol Slate and Pebble Clear Reducer or any other lacquer thinner to the surface, as this may remove the coating. To remove any grease or oil spills wipe the surface down with a rag dampened with mineral turpentine. For most other spillages thoroughly wash down the surface with water and household detergent.

MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:



(a) The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. (b) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (c) the product be used only in accordance with the information provided by Wattyl; (d) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (e) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.

4. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)