

Wattyl Estapol Sanding Sealer Hi-Build

PRODUCT DESCRIPTION

Wattyl Estapol Sanding Sealer Hi-Build is a quick drying brushing sanding sealer, which effectively seals timbers. It makes it easier for sanding and quicker finishing. Recommended for used under Wattyl Estapol Polyurethane Gloss, Satin or Matt clear finishes only.

INTENDED USES – INTERIOR

- Timber doors, wood frames, bars, bench tops, tables
- Woodwork paneling e.g. wet areas – bathrooms, kitchens, spas
- Awkward areas e.g. louvre doors, turned legs
- Furniture e.g. cabinet doors
- Exposed beams (smooth)

TECHNICAL DATA

- | | |
|-------------------------|---|
| • Vehicle Type | Urethane Alkyd |
| • Pigmentation | Fillers |
| • Solvent | Mineral Turpentine |
| • Pot Life | Not applicable |
| • Finish | Clear |
| • Colour | Clear |
| • Touch Dry Time | 1 hour at 20°C and 65% RH |
| • Recoat Time | 6 hours at 20°C and 65% RH. Allow up to twice as long for cooler and more humid conditions. |
| • Preparatory Coat | Not required |
| • Theoretical Coverage | 8 – 14m ² /L depending on porosity and texture of substrate |
| • Dry Film Thickness | 50µ |
| • Usual Number of Coats | 1 |
| • Toxicity of dry film | Non Toxic |
| • Durability | Must be top coated |
| • Thinning and Clean Up | Mineral Turpentine |
| • V.O.C. | >300 g/L as per EC-07-07 |
| • Pack Sizes | 500mL, 1L, 4L |

PERFORMANCE PARAMETERS

Features

- When applied to unfinished timber, it raises the grain for sanding purposes and aids the application of subsequent coats of Wattyl Polyurethane clear finishes.
- Can be over coated with Wattyl Estapol Polyurethane Gloss, Satin or Matt to increase surface protection without deepening the colour.

Constraints

- Do not use on flooring.
- Some timbers particularly natives such as Rimu, Totara and Matai are best sealed after staining with Wattyl Estapol Speed Clear to prevent slow drying should a turpentine based polyurethane be used as a finish.

SURFACE PREPARATION

Surfaces to be coated should be thoroughly cleaned, be dry, free from wax, grease, dust and have been thoroughly sanded. Nail holes or cracks should be filled with Wattyl Colourwood Timber Putty, allowed to dry and sanded smooth.

Stain bare timber if desired with Wattyl Colourwood Pigmented Stain or Wattyl Colourwood Dye Stain and allow to dry in accordance to relevant directions.

APPLICATION

Stir thoroughly with a flat stick before use.

Wattyl Estapol Sanding Sealer Hi-Build may be applied by brush, speed brush, or spray equipment. Sand lightly before recoating.

On open grained timbers an extra coat may be required to give a smoother finish.

NOTES

Like all oil based products, under some conditions the drying character of this product can be slowed by natural oils and waxes occurring in certain timbers such as Rimu, Totara and Matai. This will be noticed by clogging of sandpaper or lifting of the previous coating.

We advise testing these surfaces before recoating. If problems are found seal the piece with Wattyl Estapol Speed Clear before proceeding.

Wattyl Estapol Sanding Sealer Hi-Build appears milky in the can but dries to a perfectly clear finish.

MATERIAL SAFETY DATA SHEETS

Wattyl (N.Z) Ltd Material Safety Data Sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products, and are available on request.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:



(a) The user should check the date of printing, and if more than 24 months have elapsed, should verify with our nearest sales office that the information is still current. (b) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (c) the product be used only in accordance with the information provided by Wattyl; (d) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (e) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.

2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.

3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.

4. Because we cannot control the way these products may be used, or the conditions they may be exposed to, we can give no express guarantees in respect of these products or their performance. However certain guarantees may be implied by law.

Wattyl (N.Z.) Limited, P. O. Box 1545, Auckland, 1. Phone 09 820 6700 Fax 09 820 6572



WATTYL (NZ) LTD

INFORMATION HELP LINE: 0800 735551 (New Zealand)